

FOND DU LAC DIMENSIONAL

Application	Available	Recommended for Interior Use	Recommended for Exterior Use
Full Bed Depth Veneer (±4")	Yes	Yes	Yes
Thin Veneer (±1")	Yes	Yes	Yes
Thin Veneer Corners	Yes	Yes	Yes

ASTMs

ASTM C-97 • Absorption & Bulk Specific Gravity

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170 • Compressive Strength

Parallel to Rift, Dry	36,100 psi
Parallel to Rift, Wet	32,000 psi
Perpendicular to Rift, Dry	35,800 psi
Perpendicular to Rift, Wet	30,000 psi







ASTM C-99 • Modulus of Rupture

Parallel to Rift, Dry	3,770 psi
Parallel to Rift, Wet	3,500 psi

ASTM C-880 • Flexural Strength

Perpendicular to Rift, Dry	1,780 psi
Perpendicular to Rift, Wet	1,730 psi

SPECIFICATIONS

 100% BEDFACE
 PATTERN Dimensional Ashlar Random Ashlar
 HEIGHT Dimensional: 2.25" • 5" • 7.75" • 10.5"
 LENGTH Random, from 8"-48" (Thin Veneer: 8"-24")
 COVERAGE Full Bed Depth Veneer: 35-40 Square Feet Per Ton
 COLOR Light and medium grays

