

# FOND DU LAC MOSAIC

| Application                 | Available | Recommended for Interior Use | Recommended for Exterior Use |
|-----------------------------|-----------|------------------------------|------------------------------|
| Full Bed Depth Veneer (±4") | Yes       | Yes                          | Yes                          |
| Thin Veneer (±1")           | Yes       | Yes                          | Yes                          |
| Thin Veneer Corners         | Yes       | Yes                          | Yes                          |

## ASTMs

### ASTM C-97 • Absorption & Bulk Specific Gravity

|                       |      |
|-----------------------|------|
| Water Absorption %    | .31  |
| Bulk Specific Gravity | 2.83 |

### ASTM C-99 • Modulus of Rupture

|                       |           |
|-----------------------|-----------|
| Parallel to Rift, Dry | 3,770 psi |
| Parallel to Rift, Wet | 3,500 psi |







### ASTM C-170 • Compressive Strength


|                            |            |
|----------------------------|------------|
| Parallel to Rift, Dry      | 36,100 psi |
| Parallel to Rift, Wet      | 32,000 psi |
| Perpendicular to Rift, Dry | 35,800 psi |
| Perpendicular to Rift, Wet | 30,000 psi |

### ASTM C-880 • Flexural Strength

|                            |           |
|----------------------------|-----------|
| Perpendicular to Rift, Dry | 1,780 psi |
| Perpendicular to Rift, Wet | 1,730 psi |

## SPECIFICATIONS

|   |  |
|---|--|
|  | <b>Naturally irregular bedface pieces from the quarry</b>        |
|  | <b>PATTERN</b> Irregular   |
|  | <b>HEIGHT</b> Irregular, 10"x10" - 16"x16"                       |
|  | <b>LENGTH</b> Random, from 10"-16"                               |
|  | <b>COVERAGE</b> Full Bed Depth Veneer: 30-40 Square Feet Per Ton |
|  | <b>COLOR</b> Light and medium grays with amber accents           |



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101



**GOLD QUARRIER**  
 ANSI/NSC 373-2013  
 C0290908-101