

# GRAPHITE MANOR

Application	Available	Recommended for Interior Use	Recommended for Exterior Use
Full Bed Depth Veneer (±4")	Yes	Yes	Yes
Thin Veneer (±1")	Yes	Yes	Yes
Thin Veneer Corners	Yes	Yes	Yes

## ASTMs

### ASTM C-97 • Absorption & Bulk Specific Gravity

Water Absorption %	.31
Bulk Specific Gravity	2.83

### ASTM C-99 • Modulus of Rupture

Parallel to Rift, Dry	3,770 psi
Parallel to Rift, Wet	3,500 psi







### ASTM C-170 • Compressive Strength

Parallel to Rift, Dry	36,100 psi
Parallel to Rift, Wet	32,000 psi
Perpendicular to Rift, Dry	35,800 psi
Perpendicular to Rift, Wet	30,000 psi

### ASTM C-880 • Flexural Strength

Perpendicular to Rift, Dry	1,780 psi
Perpendicular to Rift, Wet	1,730 psi

## SPECIFICATIONS

 <b>100% BEDFACE</b>
 <b>PATTERN</b> Dimensional Ashlar   Random Ashlar
 <b>HEIGHT</b> Snapped: 4"-12"
 <b>LENGTH</b> Random, from 8"-30" (Thin Veneer: 8"-24")
 <b>COVERAGE</b> Full Bed Depth Veneer: 35-40 Square Feet Per Ton
 <b>COLOR</b> light to dark silver and graphite gray

