

# HAMILTON COUNTRY

| Application                 | Available | Recommended for Interior Use | Recommended for Exterior Use |
|-----------------------------|-----------|------------------------------|------------------------------|
| Full Bed Depth Veneer (±4") | Yes       | Yes                          | Yes                          |
| Thin Veneer (±1")           | Yes       | Yes                          | Yes                          |
| Thin Veneer Corners         | Yes       | Yes                          | Yes                          |

## ASTMs

### ASTM C-97 • Absorption & Bulk Specific Gravity

|                       |      |
|-----------------------|------|
| Water Absorption %    | 1.60 |
| Bulk Specific Gravity | 2.54 |







### ASTM C-170 • Compressive Strength

|                            |            |
|----------------------------|------------|
| Parallel to Rift, Dry      | 15,100 psi |
| Parallel to Rift, Wet      | 13,200 psi |
| Perpendicular to Rift, Dry | 15,100 psi |
| Perpendicular to Rift, Wet | 14,400 psi |

### ASTM C-99 • Modulus of Rupture

|                            |           |
|----------------------------|-----------|
| Parallel to Rift, Dry      | 1,110 psi |
| Parallel to Rift, Wet      | 1,110 psi |
| Perpendicular to Rift, Dry | 1,780 psi |
| Perpendicular to Rift, Wet | 2,060 psi |

## SPECIFICATIONS

|  |
|--|
|  <b>100% SPLIT FACE</b>   |
|  <b>PATTERN</b> Dimensional Ashlar   Random Ashlar                |
|  <b>HEIGHT</b> Varies from 2"-9"                                  |
|  <b>LENGTH</b> Random, from 8"-36" (Thin Veneer: 8"-24")          |
|  <b>COVERAGE</b> Full Bed Depth Veneer: 35-40 Square Feet Per Ton |
|  <b>COLOR</b> Gray with hints of buff                             |

