

HERITAGE DIMENSIONAL

Application	Available	Recommended for Interior Use	Recommended for Exterior Use
Full Bed Depth Veneer (±4")	Yes	Yes	Yes
Thin Veneer (±1")	Yes	Yes	Yes
Thin Veneer Corners	Yes	Yes	Yes

ASTMs

ASTM C-97 • Absorption & Bulk Specific Gravity

Water Absorption %	.50
Bulk Specific Gravity	2.79







ASTM C-99 • Modulus of Rupture

Parallel to Rift, Dry	2,040 psi
Parallel to Rift, Wet	1,690 psi

ASTM C-170 • Compressive Strength

Parallel to Rift, Dry	21,300 psi
Parallel to Rift, Wet	20,300 psi
Perpendicular to Rift, Dry	29,400 psi
Perpendicular to Rift, Wet	29,100 psi

SPECIFICATIONS

	60% BEDFACE, 40% SPLIT FACE
	PATTERN Dimensional Ashlar Random Ashlar
	HEIGHT Dimensional: 2.25" • 5" • 7.75" • 10.5"
	LENGTH Random, from 8"-48" (Thin Veneer: 8"-24")
	COVERAGE Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	COLOR Golden buff and light to medium brown

