

HERITAGE MANOR

Application	Available	Recommended for Interior Use	Recommended for Exterior Use
Full Bed Depth Veneer (±4")	Yes	Yes	Yes
Thin Veneer (±1")	Yes	Yes	Yes
Thin Veneer Corners	Yes	Yes	Yes

ASTMs

ASTM C-97 • Absorption & Bulk Specific Gravity

Water Absorption %	.50
Bulk Specific Gravity	2.79







ASTM C-99 • Modulus of Rupture

Parallel to Rift, Dry	2,040 psi
Parallel to Rift, Wet	1,690 psi

ASTM C-170 • Compressive Strength

Parallel to Rift, Dry	21,300 psi
Parallel to Rift, Wet	20,300 psi
Perpendicular to Rift, Dry	29,400 psi
Perpendicular to Rift, Wet	29,100 psi

SPECIFICATIONS

 100% BEDFACE
 PATTERN Dimensional Ashlar Random Ashlar
 HEIGHT Snapped: 4"-12"
 LENGTH Random, from 8"-30" (Thin Veneer: 8"-24")
 COVERAGE Full Bed Depth Veneer: 35-40 Square Feet Per Ton
 COLOR Golden buff and light to medium brown

