

HERITAGE MOSAIC

Application	Available	Recommended for Interior Use	Recommended for Exterior Use
Full Bed Depth Veneer (±4")	Yes	Yes	Yes
Thin Veneer (±1")	Yes	Yes	Yes
Thin Veneer Corners	Yes	Yes	Yes

ASTMs

ASTM C-97 • Absorption & Bulk Specific Gravity

Water Absorption %	1.60
Bulk Specific Gravity	2.54







ASTM C-170 • Compressive Strength

Parallel to Rift, Dry	15,100 psi
Parallel to Rift, Wet	13,200 psi
Perpendicular to Rift, Dry	15,100 psi
Perpendicular to Rift, Wet	14,400 psi

ASTM C-99 • Modulus of Rupture

Parallel to Rift, Dry	1,110 psi
Parallel to Rift, Wet	1,110 psi
Perpendicular to Rift, Dry	1,780 psi
Perpendicular to Rift, Wet	2,060 psi

SPECIFICATIONS

	Naturally irregular bedface pieces from the quarry
	PATTERN Irregular
	HEIGHT Irregular, 10"x10" - 16"x16"
	LENGTH Random, from 10"-20"
	COVERAGE Full Bed Depth Veneer: 30-40 Square Feet Per Ton
	COLOR Golden buff and light to medium brown



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101



GOLD QUARRIER
 ANSI/NSC 373-2013
 C0290908-101